



HAYCARB
Activated carbon solutions

Haycarb Water Series

Desalination Systems

RIWD 1001 — STANDARD PRODUCT SPECIFICATION

PARAMETER	VALUE	TEST METHOD
Carbon Tetrachloride Adsorption (% by wt)	Min: 55	ASTM
Iodine Number (mg/g)	Min: 1100	ASTM
Apparent Density (g/cc)	Min: 0.48	ASTM
Moisture (% wt/wt)	Max: 5	ASTM
Ash (% wt)	Max: 3	ASTM
pH	9-11	ASTM
Hardness No	Min: 98	ASTM
Particles size 12x40 US mesh		ASTM
> 12 mesh (1.70 mm) (% wt/wt)	Max: 5	
12x40 mesh (1.70 mmx 0.425 mm) (% wt/wt)	Min: 90	
< 40 mesh (0.425 mm) (% wt/wt)	Max: 5	



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU
Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com